

# Global Automotive Window Films

Product	Film Construction	Color	Adhesive	# of Plies	Thickness	Warranty*	VLT	Glare Reduction	UV Rejection	Total Solar Energy Rejected
---------	-------------------	-------	----------	------------	-----------	-----------	-----	-----------------	--------------	-----------------------------

## NR Quick Dry Plus

NR Quick Dry Plus 5%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	6%	93%	99%	42%
NR Quick Dry Plus 15%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	16%	82%	99%	41%
NR Quick Dry Plus 20%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	19%	79%	99%	40%
NR Quick Dry Plus 30%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	30%	67%	99%	35%
NR Quick Dry Plus 35%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	35%	62%	99%	34%
NR Quick Dry Plus 40%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	39%	57%	99%	33%
NR Quick Dry Plus 45%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	45%	51%	99%	32%
NR Quick Dry Plus 50%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	49%	46%	99%	30%
NR Quick Dry Plus 55%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	55%	40%	99%	29%

## HP Charcoal Premium

HP Charcoal Premium 5%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	5%	94%	99%	61%
HP Charcoal Premium 10%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	10%	89%	99%	53%
HP Charcoal Premium 20%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	20%	78%	99%	51%
HP Charcoal Premium 30%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	28%	69%	99%	43%
HP Charcoal Premium 40%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	39%	57%	99%	41%
HP Charcoal Premium 45%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	44%	52%	99%	39%
HP Charcoal Premium 50%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	54%	41%	99%	34%

## QDP Ceramic

QDP Ceramic 5%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	4%	96%	99%	66%
QDP Ceramic 18%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	18%	80%	99%	62%
QDP Ceramic 33%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	32%	65%	99%	58%
QDP Ceramic 38%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	38%	58%	99%	56%
QDP Ceramic 42%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	42%	54%	99%	53%
QDP Ceramic 46%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	46%	49%	99%	52%
QDP Ceramic 50%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	51%	44%	99%	51%
QDP Ceramic 70%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	69%	24%	99%	47%
QDP Ceramic 80%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	78%	14%	99%	42%
QDP Ceramic 86%	Ceramic	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	86%	6%	99%	27%

Infrared Rejection as measured at 1,025 nm. All values are as applied to 1/8" (3mm) clear glass. The performance data reported was tested using ASHRAE, ASTM, BSEN 410, and AIMCAL Standards.

\*Please see warranty for specific terms and conditions.